

Abstract:

A molding compound which comprises the following components:

- I. 50 to 99.98 parts by weight of thermoplastic polyesters,
 - 5 II. 0.02 to 5 parts by weight of a copolymer which contains polysiloxane blocks and polyester blocks,
 - III. 0 to 49.98 parts by weight of further adjuvants, selected from further polymers, fillers and pigments, antistats, reinforcing agents, and stabilizers,
- the sum of all the parts by weight making 100,
- 10 is used for producing metallized moldings.